

Data sheet: A4.2

## SUPRAFORM<sup>®</sup> HR 190 - 290

Hot Rolled Structural Steel coil with Improved Formability

### General description

SUPRAFORM<sup>®</sup> HR is a range of hot rolled structural steels with improved formability and good weldability.

The SUPRAFORM<sup>®</sup> HR range consists of four grades where the HR designations relate to the minimum respective yield strengths of each grade.

SUPRAFORM<sup>®</sup> HR has been developed mainly for applications where pressing, stamping or forming has to be carried out on structural steel to produce a final product. Although the SUPRAFORM<sup>®</sup> HR grades are essentially structural steel grades they perform very well in drawing and forming applications. For example SUPRAFORM<sup>®</sup> HR 190 has mechanical and forming properties similar to EN 10111 DD14, a drawing steel.

SUPRAFORM<sup>®</sup> HR can be welded using any of the standard arc and resistance welding processes, usually without any special precautions.

Some typical applications are:

- Body and chassis components for the automotive industry, bumper brackets, engine mounting brackets and wheel centres.
- Any cold formed sections requiring sharp bends.
- Container internal structures.

### Chemical composition

Table 1. Chemical composition specification (ladle analysis, percent) for the thickness range 2,0 - 13,0 mm<sup>1</sup>

Grade	C max	Mn max	P max	S max
HR 190	0,08	0,40	0,020	0,020
HR 220	0,10	0,90	0,020	0,020
HR 250	0,16	1,00	0,020	0,020
HR 290 <sup>1</sup>	0,21	1,10	0,020	0,020
HR 290 (S 0,01) <sup>2</sup>	0.21	1.50	0.020	0.010

Note:

1. Maximum thickness is 6,0mm.
2. Maximum thickness is 4,0mm.

For further information, contact:

ArcelorMittal South Africa, PO Box 2, Vanderbijlpark 1900. Toll free number 0800 005043,.

Care has been taken to ensure that the information in this data sheet is accurate. ArcelorMittal South Africa Limited does not, however, assume responsibility for any inaccuracies or misinterpretations of this data. We are continuously engaged in product development and revised data sheets will be issued from time to time. Please ensure that you have the most recent issue. Effective date: December 2015

In order to assist end-users in determining fabrication parameters, the typical chemical compositions used to achieve the desired mechanical properties are given in Table 2:

Table 2. Typical chemical composition (ladle analysis, percent)

Grade	C	Mn	Si	Al	P	S
HR 190	0,04	0,20	0,03	0,04	0,015	0,015
HR 220	0,05	0,25	0,03	0,04	0,015	0,015
HR 250	0,12	0,55	0,03	0,04	0,015	0,015
HR 290	0,16	0,85	0,03	0,04	0,015	0,015
HR 290 (S 0,01)	0.15	0.92	0.02	0.04	0.014	0.004

### Mechanical properties

Table 3a. Mechanical properties

Grade	Yield strength (MPa)	Minimum tensile strength <sup>1</sup> (MPa)	Minimum elongation <sup>2</sup> (%) for thickness <i>t</i> (mm)		Mandrel diameter for 180° bend test <sup>3</sup> for strip thickness <i>t</i> (mm)	
			2 ≤ <i>t</i> ≤ 4	4 < <i>t</i> ≤ 13	<i>t</i> ≤ 4	<i>t</i> > 4
HR 190	190 - 270	290	35	37	0 <i>t</i>	0 <i>t</i>
HR 220	220 - 300	320	32	34	0 <i>t</i>	0 <i>t</i>
HR 250	250 - 330	370	30	33	0 <i>t</i>	1 <i>t</i>
HR 290 <sup>4</sup>	290 - 370	410	27	30	1 <i>t</i>	1,5 <i>t</i>

Table 3b. Mechanical properties

Grade	Yield strength (MPa)	Minimum tensile strength <sup>1</sup> (MPa)	Elongation 50m gauge length (%)			
			2.0 - 2.49mm	2.5-3.14mm	3.15-3.99mm	4.00mm
HR 290 (S 0,01) <sup>5</sup>	290 - 390	440	30	32	33	34

#### Notes:

1. Tensile test to EN 10002 Part 1 (1990)
2. Gauge length 50mm.
3. The sample specimens will be free of cracks on the outside of the bend when tested to BS 1639.
4. Maximum thickness is 6,0mm.
5. Maximum thickness is 4,0mm.

### Dimensions

SUPRAFORM<sup>®</sup> HR is available in the dimensions indicated in the data sheet: Hot Strip Mill Product Dimensions (file reference A1.1).

In order to possess good drawing, forming and pressing properties, hot rolled strip must have a homogeneous microstructure which can be achieved only if the strip temperature is accurately controlled during hot rolling. This becomes difficult when the thickness is less than 2,0mm. Therefore, if thinner material is required, cold rolled strip should be used.

### Dimensional tolerances

For dimensional tolerances, refer to the data sheet: Hot Strip Mill Product Tolerances (file reference A1.2).

For further information, contact:

ArcelorMittal South Africa, PO Box 2, Vanderbijlpark 1900. Toll free number 0800 005043.

Care has been taken to ensure that the information in this data sheet is accurate. ArcelorMittal South Africa Limited does not, however, assume responsibility for any inaccuracies or misinterpretations of this data. We are continuously engaged in product development and revised data sheets will be issued from time to time. Please ensure that you have the most recent issue. Effective date: December 2015

## Certification

All material described in this data sheet is supplied with test and analysis certificates.

## Supply conditions

All material described in this data sheet is supplied in terms of Price Lists 120 and 121 and ArcelorMittal South Africa's General Conditions of Sale.

For further information, contact:

ArcelorMittal South Africa, PO Box 2, Vanderbijlpark 1900. Toll free number 0800 005043.

Care has been taken to ensure that the information in this data sheet is accurate. ArcelorMittal South Africa Limited does not, however, assume responsibility for any inaccuracies or misinterpretations of this data. We are continuously engaged in product development and revised data sheets will be issued from time to time. Please ensure that you have the most recent issue. **Effective date: December 2015**