

Data sheet: B6.1

Enamelling steels

Cold Rolled Steel Sheet for Enamelling Applications

General description

Cold rolled steel sheet for enamelling applications is produced by ArcelorMittal South Africa. Enamelling steel is suitable for high temperature baked enamel applications such as pots, pans, kettles, dishes, geysers and basins. The following types are available:

- EN 10209 DC01EK / Commercial Enamelling Quality - suitable for applications where severe forming is not required.
- EN 10209 DC04EK / Drawing Enamelling Quality - drawing steels for general drawing and enamelling applications.

The choice of steel depends on the degree of formability required, and the type of enamelling process to be used.

Enamelling steels are readily weldable. A heat input of 0,32 kJ/mm is recommended by AWS D1.3.

Chemical composition

Table 1: Chemical composition specification (ladle analysis, percent)

| Specification | C Max | Mn max | P max | S max | Si Max | Al | N max |
|-------------------------------|----------|-----------|----------|----------|-----------|----|----------|
| Commercial Enamelling Quality | 0,10 | 0,45 | 0,040 | 0,040 | 0,030 | - | 0,008 |
| Drawing Enamelling Quality | 0,08 | 0,40 | 0,030 | 0,035 | 0,030 | - | 0,008 |
| EN 10209 DC01EK | 0,08 | 0,45 | 0,040 | 0,040 | 0,030 | - | 0,008 |
| EN 10209 DC04EK | 0,08 | 0,40 | 0,030 | 0,035 | 0,030 | - | 0,008 |

Mechanical properties

Table 2: Mechanical properties

| Specification | Yield Strength ² (MPa) Max | Tensile strength (MPa) Min | Elongation (%) ^{1, 2} Min | Mandrel diameter for 180° bend test for strip thickness <i>t</i> |
|-------------------------------|--|-------------------------------------|--|---|
| Commercial Enamelling Quality | - | - | - | 0 <i>t</i> |
| Drawing Enamelling Quality | 210 | 270 - 350 | 34 | |
| EN 10209 DC01EK | 270 | 270 - 390 | 30 | |
| EN 10209 DC04EK | 210 | 270 - 350 | 36 | |

Notes:

1. Values apply to material thicker than 0,70mm.
2. The minimum guaranteed elongation is reduced by 2,0%, and the maximum Yield strength is increased by 20MPa for every 0,2mm (or part thereof) thickness reduction below (and including) *t* = 0,70mm

For further information, contact:

ArcelorMittal South Africa Limited, PO Box 2, Vanderbijlpark 1900. Toll free number 0800 005043, Fax (016) 889-0070
e-mail address: datasheets@mittalsa.com

Care has been taken to ensure that the information in this data sheet is accurate. ArcelorMittal South Africa Limited does not, however, assume responsibility for any inaccuracies or misinterpretations of this data. We are continuously engaged in product development and revised data sheets will be issued from time to time. Please ensure that you have the most recent issue. Effective date: May 2013

- The tensile test is carried out as described in EN 10002 Part 1 using type 2 specimens (initial gauge length $L_0 = 80\text{mm}$). The test pieces for the tensile test are taken at right angles to the direction of rolling. Yield strength is determined by the 0,2% offset method.

Dimensions

Table 3: Available dimensions

| Thickness t (mm) | Width (mm) |
|-------------------------|---------------|
| $0,40 \leq t < 0,50$ | 800 - 1250 |
| $0,50 \leq t < 0,60$ | 800 - 1300 |
| $0,60 \leq t \leq 2,00$ | 800 - 1600 |

Notes:

- Thicknesses and widths are available in increments in accordance with Price List 130.
- Within the ranges shown in the above table, certain specific sizes are Standard Items (refer to Price List 130). Standard Items are preferentially priced and are available in smaller quantities than non-standard items.

Surface texture

Enamelling steels are available in 'normal' or 'matt' surface texture as listed in Data Sheet: Cold Rolled Products (file reference B1). A matt finish is recommended to ensure proper adhesion of the enamel coating to the base metal.

Dimensional tolerances

Tolerances on shape and dimensions are given in Data Sheet: Cold Rolled Product Tolerances (file reference B1.1).

Coil inside diameter

The standard inside diameter is 508mm (610mm on enquiry).

Sag resistance

The end-user is advised to select the material thickness with care to reduce the possibility of sagging during baking operations.

Certification

Test and analysis certificates are supplied for Drawing Enamelling Quality and Commercial Enamelling Quality.

Supply conditions

Cold rolled enamelling steel sheet is supplied in terms of Price List 130 and ArcelorMittal South Africa's General Conditions of Sale.

For further information, contact:

ArcelorMittal South Africa Limited, PO Box 2, Vanderbijlpark 1900. Toll free number 0800 005043, Fax (016) 889-0070
e-mail address: datasheets@mittalsa.com